

6PPD-q Testing on TTII PRO-MAX 37 TPE Feb 2024

Manufacturing Batch	Sample Number	SPLP Extraction Date	Analysis Date	Matrix	Analysis Method	Results	Units	Qualifier	Method Detection Limit (MDL)	Reporting Detection Limit (RDL)
Batch 21020	Sample 1	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 21020	Sample 2	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 21020	Sample 3	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22659	Sample 1	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22659	Sample 2	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	5 0.0023	ug/L	<rdl< td=""><td>0.002</td><td>0.01</td></rdl<>	0.002	0.01
Batch 22659	Sample 3	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22746	Sample 1	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22746	Sample 2	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	5 0.0022	ug/L	<rdl< td=""><td>0.002</td><td>0.01</td></rdl<>	0.002	0.01
Batch 22746	Sample 3	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22755	Sample 1	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22755	Sample 2	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	0.0031	ug/L	<rdl< td=""><td>0.002</td><td>0.01</td></rdl<>	0.002	0.01
Batch 22755	Sample 3	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22669	Sample 1	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22669	Sample 2	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01
Batch 22669	Sample 3	2024-02-19	2024-02-23	LA OTHR WTR	6PPDQ by LCMS	Not detected	ug/L	<mdl< td=""><td>0.002</td><td>0.01</td></mdl<>	0.002	0.01

These test results are for 5 manufacturing batches of Pro-Max 37 TPE with 3 sample replicates taken from each batch.

The 6PPD-Q analysis was conducted by a non-accredited laboratory on leachates of Pro-Max 37 TPE produced through a Synthetic Precipitation Leaching Procedure (SPLP) at Analytical Resources, LLC.